



# DANOCRET® PROTECT 300 Flex

**FLEXIBLE CEMENTITIOUS MEMBRANE FOR WATERPROOFING POTABLE WATER TANKS, LIFT SHAFTS, SWIMMING POOLS, TERRACES, UNIQUE POINTS AND SURFACE PROTECTION FOR CONCRETE. ONE-COMPONENT**



20KG 5KG

## TOOLS



## PERFORMANCE

± 3 kg/m<sup>2</sup>

## DRYING TIME



Made with sulphate-resistant cement



Waterproof



Effective with pressurised water



Resistant to cold/heat



Suitable for potable water



High flexibility



Stops fissures



High adherence

DANOCRET® Protect 300 Flex is a flexible, waterproof, one-component PCC cementitious membrane to protect the surface and waterproof concrete and mortar. Made with a base of hydraulic binders, selected aggregates and polymers that grant it excellent elasticity, adherence and waterproofing ability.

## ADVANTAGES

- Waterproof.
- Trafficable system under tile.
- High flexibility and adherence.
- Elasticity that ensures crack bridging of up to 1.26 mm.
- Very high adherence in non-glazed supports (2.5 N/mm<sup>2</sup>, method EN 1542).
- Resistant to negative pressures (up to 5.5 atm) and positive pressures.
- Resistant to frosting/thawing cycles.
- Prevents damp caused by condensation and the appearance of efflorescence.
- High protection against saltpetre and sea water according to UNE EN 1504-2.
- Compatible with potable water, Royal Decree 3/2023.
- Suitable for protection against carbonation.
- Compatible with ARGOCOLA® ELITE 500 C2TE S1.

## APPLICATION

- Waterproofing terraces, balconies and windowsills.
- Waterproofing bathrooms, kitchens and swimming pools before installing the final cladding.
- Suitable for reducing damp caused by capillarity in buried structures and lift shafts.
- Effective as a waterproof, flexible barrier for renders with micro-fissures.
- Protection of concrete surfaces against sea water and salts.

## SUPPORTS

- Concrete and mortar renders.
- Ceramic and natural stone cladding.
- Plasterboard.

## FLEXIBLE CEMENTITIOUS MEMBRANE FOR WATERPROOFING POTABLE WATER TANKS, LIFT SHAFTS, SWIMMING POOLS, TERRACES, UNIQUE POINTS AND SURFACE PROTECTION FOR CONCRETE. ONE-COMPONENT

### APPLICATION METHOD

- Before applying the product, check the application surface is dry, clean and free from solid remains or irregularities.
- Protect yourself when handling components by wearing the right gloves and mask. Consult the safety data sheet.
- Mix DANOCRET® Protect 300 Flex with 29% - 30% of clean water (5.8 - 6 L per 20 kg bag) preferably by mechanical means until a homogeneous, creamy, lump-free mixture with a thick paint consistency is achieved.
- Apply to fissures and joints first. We recommend using the 2,5 x 2,5 mm glass fibre mesh MALLA FV 60.
- If reinforcing, use a trowel/roller/spraying machine to apply the first coat and install glass fibre mesh 60 reinforcement, including on the angles, before it dries.
- Apply all other coats intersecting the previous coat for a better result (consult drying time).

### APPLICATION TEMPERATURE

- Between 8°C and 30°C.

### DRYING TIME

- To apply another coat:  
Summer: 4 h Winter: 6 to 8 h
- For coats: 48 h at 20°C, 5 days at 10°C.

### STORAGE AND SHELF LIFE

- Keep the package hermetically sealed and protected from extreme temperatures and sun exposure.
- Store the product between 5°C and 30°C for a maximum of 12 months.

### PRECAUTIONS

- Once the mix has been made, it must be applied in a maximum of 30 minutes.
- We recommend applying a minimum of two coats of product with each coat at least 1 mm thick.
- Trafficable after 24-48 hours of drying.
- Wet porous supports well before applying the first coat as a primer.
- Entry into service must be later than seven days if in contact with water.
- Clean tools with water as soon as you have finished. If they have any solid remains, scrape these off.
- Do not apply to hot supports or when there is a chance of rain.
- Perform material assessments to ensure correct performance and prevent an accumulation of material by preparing the supports and creating half-pipes with the most suitable product from the ARGOTEC® REPAIR range. If a half-pipe cannot be made on the straight angles, use DANOBAND® Butyl.

### TECHNICAL DATA

Appearance	PCC mortar (cement, aggregates and additives)
Colour	White / Grey
Bulk density	1.50 ± 0.05 kg/dm <sup>3</sup>
pH	10.5 ± 0.5
Solids content (comp. B)	57 ± 2
Thickness to apply	2 mm < and < 3 mm
Thickness per coat	Never more than 2 kg/m <sup>2</sup>
Waterproof to water in liquid form and capillary absorption (EN 1062-3)	$W = 0.04 \text{ kg}/(\text{m}^2 \cdot \text{h}^{0.5})$
Negative pressure	Up to 5.5 atm
Resistant to cracking (EN 1062-7)	Class A4 (at 0°C)
Crack elongation capacity (EN 14891 Sec. A.8.2)	1.26 mm (coat of 2 mm at 23°C)
Direct traction adherence (EN 1504-1:2005)	1.8 N/mm <sup>2</sup> (method EN 1542)
Adherence after thermal compatibility (EN 13687-1 and 2)	1.5 N/mm <sup>2</sup> (method EN 1542)
Classification according to EN 14891 table 4	MC01P
Permeability to CO <sub>2</sub> in m (EN 1062-6 2003)	Class III
Permeability to water vapour (EN ISO 7783.2018)	Class I