

ARGONIV® 120 ÉLITE



SELF-LEVELLING
MORTAR

SELF-LEVELING, QUICK-DRYING PASTE FOR MEDIUM THICKNESSES



UNE EN 13813
CT C35 F10

25KG

ARGONIV® 120 ÉLITE is a self-leveling mortar based on hydraulic binders, selected aggregates, polymers, and chemical additives that give it extraordinary pumping and leveling properties as well as excellent mechanical properties in short times.

ADVANTAGES

- Fast hardening without cracking.
- No segregation (great strength regarding different amounts of water).
- Low dynamic stress.
- Suitable for aesthetic requirements.
- Trafficable after 5 hours.
- Humidity less than 3% after 48 hours.
- High self-leveling power.
- Thicknesses 10 - 40 mm.
- Surface suitable for covering with carpet, ceramic, paint, etc.
- High mechanical performance.
- Interiors.
- Suitable for IMPACTODAN® BT, system, with thicknesses less than 20 mm, reinforced with DANOTHERM® Malla PX 160.

SUPPORT

- Concrete floor slabs.
- Mortar floor slabs
- Floor slabs with anti-impact or acoustic membrane.
- Other cement-based supports.

USES

- Leveling of medium thickness in interior floors in new construction and rehabilitation.
- Creation of surfaces for the placement of ceramic coatings, natural stone, and other coatings.
- Creation of floor slabs in industrial and commercial sectors, fit to be sealed with suitable paints and varnishes.

PREPARATION OF THE SUPPORT

The support must be dry, clean, compact, free of dust and release agents. Before mechanical preparation, all traces of varnish, waxes, fats, oils and similar contaminant substances must be removed. Contaminated concrete surfaces must be mechanically treated, either by sanding, diamond sanding, blasting, or sandblasting, and then vacuumed.

For more information, consult technical department.

ARGONIV® 120 ÉLITE

SELF-LEVELING, QUICK-DRYING PASTE FOR MEDIUM THICKNESSES

APPLICATION METHOD

- Mix ARGONIV® 120 ÉLITE with 4.75 L of clean water per bag of 25 kg, preferably by mechanical means, until a homogeneous, creamy, and lump-free mixture is obtained.
- Pour the mass on the support until reaching the required thickness level.
- Pass a horizontal bar in vibration mode over the material in order to facilitate the exit of the air trapped in the mortar and complete the leveling process.
- Sand and vacuum the surface before the final coating, if necessary.

APPLICATION TEMPERATURE

- Suitable temperature between 15 °C and 25 °C.

PRESENTATION AND CONSERVATION

ARGONIV® 120 ÉLITE is packed in multilayer paper bags of 25 kg with anti-humidity layer that allow its correct conservation during 12 months in its closed original package safe from humidity.

PRECAUTIONS

- Do not apply on plaster supports.
- Do not apply on plastic, metal, wood, rubber, etc. surfaces
- The suitable temperature range for the application of the product is between 15 °C and 25 °C, with a relative humidity between 60 - 75%. Do not apply below 5 °C or above 30 °C.
- Do not apply with risk of frost, rain, strong wind, or direct sunlight.
- Protect the fresh surface from direct sunlight, rain and especially from airflows.
- Do not apply on floors with permanent humidity.
- On low porous substrates prime with DANOPRIMER® EP.
- On very porous substrates prime with DANOPRIMER® RPU.

DESCRIPTION

The leveling of interior floors with a thickness between 10 and 40 mm will be carried out with the dry mortar ARGONIV® 120 ÉLITE from the company DANOSA, class CT C35 F10 according to the standard UNE EN 13813: 2003. The application support must be healthy, clean, completely hardened and must have finished its time of dimensional change. Work joints must be respected.

TECHNICAL DATA

Identification and application data	
Appearance	Powder
Colour	Grey
Apparent density	1,50 kg/L
Particle size range	0/0,2 mm
Mixing water	19 %
Flow characteristics	135 mm
Minimum thickness	10 mm
Maximum thickness	40 mm
Performance	18 kg/m ² and cm of thickness
Workability	30 min
Trafficability	5 hours
Performance data	
Classification according to UNE EN 13813	CT C35 F10
Compression strength 5 hours	≥ 10,0 MPa
Compression strength 24 hours	≥ 20,0 MPa
Compression strength 7 days	≥ 24,0 MPa
Compression strength 28 days	≥ 35,0 MPa
Reaction to fire	F