

PRODUCT DATA SHEET

|                                                   |                              |  |         |                |          |
|---------------------------------------------------|------------------------------|--|---------|----------------|----------|
| ITEM:                                             | CRYSTALLO PULIDO RECTIFICADO |  | BRAND:  | BALDOCER, S.A. |          |
| DATE:                                             | 31/10/2025                   |  | FORMAT: | 60X120 cm      |          |
| CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411) |                              |  | GROUP:  | Bla            | ANNEX: G |

FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

| UNE-EN-ISO-10545-2        | REFERENCE | RESULT                      |
|---------------------------|-----------|-----------------------------|
| DIMENSIONS                |           | 600X1200                    |
| LENGTH                    | ± 0,6 %   | 0,01% / -0,03%<br>1200,1 mm |
| WIDTH                     | ± 0,6 %   | 0,10% / -0,15%<br>599,9 mm  |
| STRAIGHTNESS OF SIDES     | ± 0,5 %   | 0,02% / -0,01%              |
| THICKNESS                 | ± 5,0 %   | 2,50% 8,9 mm                |
| RECTANGULARITY            | ± 0,5 %   | 0,10% / -0,05%              |
| CENTRAL SURFACE FLATNESS  | ± 0,5 %   | 0,14%                       |
| LATERAL SURFACE FLATNESS  | ± 0,5 %   | 0,13%                       |
| DIAGONAL SURFACE FLATNESS | ± 0,5 %   | 0,07% / -0,10%              |

PHYSICAL PROPERTIES

| UNE-EN-ISO-10545-3 |          |      |
|--------------------|----------|------|
| WATER ABSORPTION   | E ≤ 0,5% | 0,1% |

| UNE-EN-ISO-10545-4 |              |      |
|--------------------|--------------|------|
| BREAKING STRENGTH  | MIN 1300 N   | 2045 |
| MODULUS OF RUPTURE | MIN 35 N/mm² | 45   |

| UNE-EN-ISO-10545-6                                  |           |           |
|-----------------------------------------------------|-----------|-----------|
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION | NOT APPLY | NOT APPLY |

| UNE-EN-ISO-10545-7                   |             |     |
|--------------------------------------|-------------|-----|
| DETERMINATION TO ABRASION RESISTANCE | REVOLUTIONS | PEI |
|                                      | 6000        | 4   |

| UNE-EN-ISO-10545-9       |  |           |
|--------------------------|--|-----------|
| THERMAL SHOCK RESISTANCE |  | FULFILLED |

## UNE-EN-ISO-10545-11

|                    |  |           |
|--------------------|--|-----------|
| CRAZING RESISTANCE |  | FULFILLED |
|--------------------|--|-----------|

## UNE-EN-ISO-10545-12

|                  |  |           |
|------------------|--|-----------|
| FROST RESISTANCE |  | FULFILLED |
|------------------|--|-----------|

## UNE 67101

|                                                  |  |   |
|--------------------------------------------------|--|---|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS |  | 4 |
|--------------------------------------------------|--|---|

## DETERMINATION OF SLIDING RESISTANCE

|                                                |       |   |
|------------------------------------------------|-------|---|
| VALUE FOLLOWING UNE 41901-EX (PENDULUM)        | CLASS | 0 |
| VALUE FOLLOWING DIN 51130 (RAMP TEST)          | R     |   |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS |   |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E)  |       |   |

## CHEMICAL PROPERTIES

## UNE-EN-ISO-10545-13

|                                        |  |           |
|----------------------------------------|--|-----------|
| CHEMICAL RESISTANCE                    |  | FULFILLED |
| HOUSEHOLD CHEMICALS                    |  | GA        |
| SWIMMING POOL SALTS                    |  | GA        |
| HYDROCHLORIC LOW CONCENTRATION         |  | GLA       |
| CITRIC ACID                            |  | GLA       |
| POTASSIUM HYDROXIDE LOW CONCENTRATION  |  | GLA       |
| HYDROCHLORIC HIGH CONCENTRATION        |  | GHB       |
| LACTIC ACID                            |  | GHB       |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION |  | GHB       |

## UNE-EN-ISO-10545-14

|                         |  |           |
|-------------------------|--|-----------|
| RESISTANCE TO STAINS    |  | FULFILLED |
| IRON OXIDE-CHROME OXIDE |  | 5         |
| IODINE                  |  | 5         |
| OLIVE OIL               |  | 5         |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

**BALDOCER, S.A.**  
 Ctra. La Pobla Tornesa - Vall d'Alba, Km. 4  
 Tel. 964 400 033 / Fax 964 330 033  
 12192 VILAFAMES (Castellón)