

PRODUCT DATA SHEET

| | | | |
|--|-------------------------------------|----------------|----------------|
| ITEM: | PLAIN ASPHALT OFF WHITE RECTIFICADO | BRAND: | BALDOCER, S.A. |
| DATE: | 31/10/2025 | FORMAT: | 60X60 cm |
| CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411) | | GROUP: | Bla |
| | | ANNEX: | G |

FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

| | UNE-EN-ISO-10545-2 | REFERENCE | RESULT |
|---------------------------|--------------------|-----------|----------------------------|
| DIMENSIONS | | | 600X600 |
| LENGTH | | ± 0,6 % | 0,05% / -0,05% 599,4 mm |
| WIDTH | | ± 0,6 % | 0,05% / -0,05% 599,4 mm |
| STRAIGHTNESS OF SIDES | | ± 0,5 % | 0,03% / -0,05% |
| THICKNESS | | ± 5,0 % | -2,11% 9,0 mm |
| RECTANGULARITY | | ± 0,5 % | 0,08% / -0,10% |
| CENTRAL SURFACE FLATNESS | | ± 0,5 % | 0,18% |
| LATERAL SURFACE FLATNESS | | ± 0,5 % | 0,13% |
| DIAGONAL SURFACE FLATNESS | | ± 0,5 % | 0,07% / -0,06% |

PHYSICAL PROPERTIES

UNE-EN-ISO-10545-3

| | | |
|------------------|----------------|------|
| WATER ABSORPTION | $E \leq 0,5\%$ | 0,1% |
|------------------|----------------|------|

UNE-EN-ISO-10545-4

| | | |
|--------------------|--------------------------|------|
| BREAKING STRENGTH | MIN 1300 N | 2258 |
| MODULUS OF RUPTURE | MIN 35 N/mm ² | 44 |

UNE-EN-ISO-10545-6

| | | |
|---|-----------|-----------|
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION | NOT APPLY | NOT APPLY |
|---|-----------|-----------|

UNE-EN-ISO-10545-7

| | | |
|--------------------------------------|-------------|-----|
| DETERMINATION TO ABRASION RESISTANCE | REVOLUTIONS | PEI |
| | 12000 | 4 |

UNE-EN-ISO-10545-9

| | | |
|--------------------------|--|-----------|
| THERMAL SHOCK RESISTANCE | | FULFILLED |
|--------------------------|--|-----------|

UNE-EN-ISO-10545-11

| | | |
|--------------------|--|-----------|
| CRAZING RESISTANCE | | FULFILLED |
|--------------------|--|-----------|

UNE-EN-ISO-10545-12

| | | |
|------------------|--|-----------|
| FROST RESISTANCE | | FULFILLED |
|------------------|--|-----------|

UNE 67101

| | | |
|--|--|---|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS | | 5 |
|--|--|---|

DETERMINATION OF SLIDING RESISTANCE

| | | |
|--|-------|----|
| VALUE FOLLOWING UNE 41901-EX (PENDULUM) | CLASS | 1 |
| VALUE FOLLOWING DIN 51130 (RAMP TEST) | R | R9 |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS | |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E) | | |

CHEMICAL PROPERTIES

UNE-EN-ISO-10545-13

| | | |
|--|--|-----------|
| CHEMICAL RESISTANCE | | FULFILLED |
| HOUSEHOLD CHEMICALS | | GA |
| SWIMMING POOL SALTS | | GA |
| HYDROCHLORIC LOW CONCENTRATION | | GLA |
| CITRIC ACID | | GLA |
| POTASSIUM HYDROXIDE LOW CONCENTRATION | | GLA |
| HYDROCHLORIC HIGH CONCENTRATION | | GHA |
| LACTIC ACID | | GHA |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION | | GHA |

UNE-EN-ISO-10545-14

| | | |
|-------------------------|--|-----------|
| RESISTANCE TO STAINS | | FULFILLED |
| IRON OXIDE-CHROME OXIDE | | 5 |
| IODINE | | 5 |
| OLIVE OIL | | 5 |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

BALDOCER, S.A.
 Ctra. La Pobla Tornesa - Vall d'Alba, Km. 4
 Tel. 964 330 033 / Fax 964 330 033
 12192 VILAFAMÉS (Castellón)