

PRODUCT DATA SHEET

| | | | |
|--|-------------------------------|----------------|----------------|
| ITEM: | STATUARIO NATURAL RECTIFICADO | BRAND: | BALDOCER, S.A. |
| DATE: | 31/10/2025 | FORMAT: | 60X120 cm |
| CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411) | | GROUP: | Bla |
| | | ANNEX: | G |

FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

| | UNE-EN-ISO-10545-2 | REFERENCE | RESULT |
|---------------------------|--------------------|-----------|-----------------------------|
| DIMENSIONS | | | 600X1200 |
| LENGTH | | ± 0,6 % | 0,01% / -0,03% 1200,0 mm |
| WIDTH | | ± 0,6 % | 0,10% / -0,15% 599,9 mm |
| STRAIGHTNESS OF SIDES | | ± 0,5 % | 0,02% / -0,01% |
| THICKNESS | | ± 5,0 % | 2,50% 6,0 mm |
| RECTANGULARITY | | ± 0,5 % | 0,10% / -0,05% |
| CENTRAL SURFACE FLATNESS | | ± 0,5 % | 0,14% |
| LATERAL SURFACE FLATNESS | | ± 0,5 % | 0,13% |
| DIAGONAL SURFACE FLATNESS | | ± 0,5 % | 0,07% / -0,10% |

PHYSICAL PROPERTIES

UNE-EN-ISO-10545-3

| | | |
|------------------|----------------|------|
| WATER ABSORPTION | $E \leq 0,5\%$ | 0,2% |
|------------------|----------------|------|

UNE-EN-ISO-10545-4

| | | |
|--------------------|--------------------------|------|
| BREAKING STRENGTH | MIN 700 N | 2703 |
| MODULUS OF RUPTURE | MIN 35 N/mm ² | 44 |

UNE-EN-ISO-10545-6

| | | |
|---|-----------|-----------|
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION | NOT APPLY | NOT APPLY |
|---|-----------|-----------|

UNE-EN-ISO-10545-7

| | | |
|--------------------------------------|-------------|-----|
| DETERMINATION TO ABRASION RESISTANCE | REVOLUTIONS | PEI |
| | | |

UNE-EN-ISO-10545-9

| | | |
|--------------------------|--|-----------|
| THERMAL SHOCK RESISTANCE | | FULFILLED |
|--------------------------|--|-----------|

UNE-EN-ISO-10545-11

| | | |
|--------------------|--|-----------|
| CRAZING RESISTANCE | | FULFILLED |
|--------------------|--|-----------|

UNE-EN-ISO-10545-12

| | | |
|------------------|--|-----------|
| FROST RESISTANCE | | FULFILLED |
|------------------|--|-----------|

UNE 67101

| | | |
|--|--|--|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS | | |
|--|--|--|

DETERMINATION OF SLIDING RESISTANCE

| VALUE FOLLOWING UNE 41901-EX (PENDULUM) | CLASS | |
|--|-------|--|
| VALUE FOLLOWING DIN 51130 (RAMP TEST) | R | |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS | |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E) | | |

CHEMICAL PROPERTIES

UNE-EN-ISO-10545-13

| CHEMICAL RESISTANCE | | FULFILLED |
|--|--|-----------|
| HOUSEHOLD CHEMICALS | | |
| SWIMMING POOL SALTS | | |
| HYDROCHLORIC LOW CONCENTRATION | | |
| CITRIC ACID | | |
| POTASSIUM HYDROXIDE LOW CONCENTRATION | | |
| HYDROCHLORIC HIGH CONCENTRATION | | |
| LACTIC ACID | | |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION | | |

UNE-EN-ISO-10545-14

| RESISTANCE TO STAINS | | FULFILLED |
|-------------------------|--|-----------|
| IRON OXIDE-CHROME OXIDE | | |
| IODINE | | |
| OLIVE OIL | | |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

BALDOCER, S.A.
Ctra. La Pobla Tornesa - Vall d'Alba, Km. 4
Tel. 964 330 033 / Fax 964 330 033
12192 VILAFAMÉS (Castellón)