

PRODUCT DATA SHEET

|                                                   |                                      |         |                |
|---------------------------------------------------|--------------------------------------|---------|----------------|
| ITEM:                                             | ILLUSION MONTMARTRE TERRE RECTIFICAD | BRAND:  | BALDOCER, S.A. |
| DATE:                                             | 31/10/2025                           | FORMAT: | 60X120 cm      |
| CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411) |                                      | GROUP:  | BIII           |
|                                                   |                                      | ANNEX:  | L              |

FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

| UNE-EN-ISO-10545-2        | REFERENCE       | RESULT                      |
|---------------------------|-----------------|-----------------------------|
| DIMENSIONS                |                 | 600X1200                    |
| LENGTH                    | ± 0,5 %         | 0,01% / -0,03%<br>1200,0 mm |
| WIDTH                     | ± 0,5 %         | 0,10% / -0,15%<br>600,1 mm  |
| STRAIGHTNESS OF SIDES     | ± 0,3 %         | 0,02% / -0,01%              |
| THICKNESS                 | ± 10,0 %        | 2,40% 11,0 mm               |
| RECTANGULARITY            | ± 0,5 %         | 0,10% / -0,05%              |
| CENTRAL SURFACE FLATNESS  | +0,5 % / -0,3 % | 0,13%                       |
| LATERAL SURFACE FLATNESS  | +0,5 % / -0,3 % | 0,13%                       |
| DIAGONAL SURFACE FLATNESS | ± 0,5 %         | 0,07% / -0,10%              |

PHYSICAL PROPERTIES

| UNE-EN-ISO-10545-3 |           |     |
|--------------------|-----------|-----|
| WATER ABSORPTION   | E > 10,0% | 14% |

| UNE-EN-ISO-10545-4 |              |      |
|--------------------|--------------|------|
| BREAKING STRENGTH  | MIN 600 N    | 1377 |
| MODULUS OF RUPTURE | MIN 12 N/mm² | 24   |

| UNE-EN-ISO-10545-6                                  |           |           |
|-----------------------------------------------------|-----------|-----------|
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION | NOT APPLY | NOT APPLY |

| UNE-EN-ISO-10545-7                   |             |     |
|--------------------------------------|-------------|-----|
| DETERMINATION TO ABRASION RESISTANCE | REVOLUTIONS | PEI |
|                                      | ---         | --- |

| UNE-EN-ISO-10545-9       |  |           |
|--------------------------|--|-----------|
| THERMAL SHOCK RESISTANCE |  | FULFILLED |

## UNE-EN-ISO-10545-11

|                    |  |           |
|--------------------|--|-----------|
| CRAZING RESISTANCE |  | FULFILLED |
|--------------------|--|-----------|

## UNE-EN-ISO-10545-12

|                  |  |               |
|------------------|--|---------------|
| FROST RESISTANCE |  | NOT FULFILLED |
|------------------|--|---------------|

## UNE 67101

|                                                  |  |     |
|--------------------------------------------------|--|-----|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS |  | --- |
|--------------------------------------------------|--|-----|

## DETERMINATION OF SLIDING RESISTANCE

|                                                |       |     |
|------------------------------------------------|-------|-----|
| VALUE FOLLOWING UNE 41901-EX (PENDULUM)        | CLASS | --- |
| VALUE FOLLOWING DIN 51130 (RAMP TEST)          | R     | --- |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS | --- |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E)  |       |     |

## CHEMICAL PROPERTIES

## UNE-EN-ISO-10545-13

|                                        |  |           |
|----------------------------------------|--|-----------|
| CHEMICAL RESISTANCE                    |  | FULFILLED |
| HOUSEHOLD CHEMICALS                    |  | GA        |
| SWIMMING POOL SALTS                    |  | GA        |
| HYDROCHLORIC LOW CONCENTRATION         |  | GLA       |
| CITRIC ACID                            |  | GLA       |
| POTASSIUM HYDROXIDE LOW CONCENTRATION  |  | GLA       |
| HYDROCHLORIC HIGH CONCENTRATION        |  | GHA       |
| LACTIC ACID                            |  | GHA       |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION |  | GHA       |

## UNE-EN-ISO-10545-14

|                         |  |           |
|-------------------------|--|-----------|
| RESISTANCE TO STAINS    |  | FULFILLED |
| IRON OXIDE-CHROME OXIDE |  | 5         |
| IODINE                  |  | 5         |
| OLIVE OIL               |  | 5         |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

BALDOCER, S.A.  
Ctra. La Pobla Tornesa - Vall d'Alba, Km. 4  
Tel. 964 400 000 - Fax 964 330 033  
12192 VILAFAMES (Castellón)