

## PRODUCT DATA SHEET

<b>ITEM:</b> SLATE NEGRO	<b>BRAND:</b> BALDOCER, S.A.
<b>DATE:</b> 24/09/2018	<b>FORMAT:</b> 40X60
<b>CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411)</b>	<b>GROUP:</b> Bla <b>ANNEX:</b> G

### FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

UNE-EN-ISO-10545-2	REFERENCE	RESULT
DIMENSIONS		400X600
LENGTH	± 0,6 %	0,05% / -0,05% 599,4 mm
WIDTH	± 0,6 %	0,05% / -0,05% 399,6 mm
STRAIGHTNESS OF SIDES	± 0,5 %	0,05% / -0,08%
THICKNESS	± 5,0 %	-2,11% 9,5 mm
RECTANGULARITY	± 0,5 %	0,12% / -0,18%
CENTRAL SURFACE FLATNESS	± 0,5 %	-0,19%
LATERAL SURFACE FLATNESS	± 0,5 %	0,02% / -0,15%
DIAGONAL SURFACE FLATNESS	± 0,5 %	0,08% / -0,06%

### PHYSICAL PROPERTIES

#### UNE-EN-ISO-10545-3

WATER ABSORPTION	$E \leq 0,5\%$	0,1%
------------------	----------------	------

#### UNE-EN-ISO-10545-4

BREAKING STRENGTH	MIN 1300 N	2774
MODULUS OF RUPTURE	MIN 35 N/mm <sup>2</sup>	50

#### UNE-EN-ISO-10545-7

DETERMINATION TO ABRASION RESISTANCE	REVOLUTIONS	PEI
	600	2

#### UNE-EN-ISO-10545-9

THERMAL SHOCK RESISTANCE		FULFILLED
--------------------------	--	-----------

#### UNE-EN-ISO-10545-11

CRAZING RESISTANCE		FULFILLED
--------------------	--	-----------

#### UNE-EN-ISO-10545-12

FROST RESISTANCE		FULFILLED
------------------	--	-----------

## UNE 67101

DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS		8
--	--	---

## DETERMINATION OF SLIDING RESISTANCE

VALUE FOLLOWING UNE-ISO-12633 (PENDULUM)	CLASS	---
VALUE FOLLOWING DIN 51130 (RAMP TEST)	R	---
VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT)	CLASS	---
VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E)		---

## CHEMICAL PROPERTIES

### UNE-EN-ISO-10545-13

CHEMICAL RESISTANCE		FULFILLED
HOUSEHOLD CHEMICALS		GA
SWIMMING POOL SALTS		GA
HYDROCHLORIC LOW CONCENTRATION		GLA
CITRIC ACID		GLA
POTASSIUM HYDROXIDE LOW CONCENTRATION		GLA
HYDROCHLORIC HIGH CONCENTRATION		GHA
LACTIC ACID		GHA
POTASSIUM HYDROXIDE HIGH CONCENTRATION		GHA

### UNE-EN-ISO-10545-14

RESISTANCE TO STAINS		FULFILLED
IRON OXIDE-CHROME OXIDE		5
IODINE		5
OLIVE OIL		5

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

**BALDOCER, S.A.**  
Ctra. La Pobla-Vall d'Alba Km. 4  
Tel. 902 45 90 00 - Fax 964 330 033  
12192 VILLAFAMÉS (Castellón)