



Learn More



**Manufacturer:**  
ÅngströmBond®

**Product Name:**  
ÅngströmBond® AB9037 Flexible, Thixotropic, Blue Fluorescent Plastic Bonding Adhesive/Urethane, UV & Heat Cure (3cc Syringe)

**Manufacturer Part Number:**  
AB9037-3CC

▶ Click here for more details on the ÅngströmBond® AB9037 Flexible, Thixotropic, Blue Fluorescent Plastic Bonding Adhesive/Urethane, UV & Heat Cure (3cc Syringe)



ADVANCED POLYMERS FOR HIGH TECH APPLICATIONS

Adhesives

### ÅNGSTRÖMBOND® AB9037

#### Flexible, UV/Secondary Heat Cure Adhesive, Blue Fluorescing Encapsulant

##### Description:

ÅNGSTRÖMBOND® AB9037 is a flexible, acrylated urethane, thixotropic, chip encapsulant and adhesive. It fluoresces blue under black light. This UV/visible light + heat cure material can completely cure in seconds with UV and offers resistance to moisture and thermal cycling.

AB9037 has excellent adhesion to FR4, Kapton, Glass, PC boards and the substrates used for electronic components. It is especially well suited for chip on board, chip on flex, multi-chip modules and glob top applications.

##### Typical Properties:

Color:	Translucent gel (light yellow)
Viscosity @ 25°C, cps:	55,000
Hardness, Shore D:	40
Linear Shrinkage, %	2.2
Elongation at Break, %	110
Tensile at Break, psi	850
Modulus of Elasticity, psi	900
Coeff. of Exp below Tg. /°C	126
Coeff. of Exp above Tg. /°C	171
Operating Temperature, °C:	-55 to 150
Glass Transition, °C	31
Dielectric Breakdown, Volts/Mil	900
Volume Resistivity, Ohm-cm	2.95E+10
Surface Resistivity, Ohm	9.44E+10
Dissipation Factor, 1 MHz	0.03
Dielectric Constant, 1MHz	4.31
Water Absorption, %	0.9
Solids content, %	100

##### Handling Characteristics:

###### Cure time:

10 W/cm² - 1-3 seconds @320-450nm UV/Vis  
10 W/cm² - 1-3 seconds @385nm LED

Heat cure shadowed areas after exposure to UV light:

110°C – 1 hour  
120°C – 30 minutes  
150°C – 15 minutes

Note: Cure schedules can vary slightly with different applications. Speed of cure depends upon thickness and light intensity. Lamps emitting high levels of shortwave light are not recommended. Please use these numbers as a basis to develop a schedule suitable for the application.

##### Storage and Shelf Life:

Store in a cool, dark place when not in use. Do not place in view of UV light source or sunlight. Material may polymerize upon exposure to ambient light.

ÅNGSTRÖMBOND® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

**Fiber Optic Center™, Inc.** MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee -- inasmuch as conditions of use are beyond our control. The properties given are typical values and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

**Contact the professionals at Fiber Optic Center for a quote or to get more details.**

[focenter.com](http://focenter.com) • 508-992-6464 | (800) 473-4237 • [sales@focenter.com](mailto:sales@focenter.com)

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice. FOC last update 1/22/2026.