



TECHNICAL INFORMATION - ASTM

PACIFIC PEAK STONE: QUARTZITE

TECHNICAL INFORMATION		VALUE	ASTM STANDARDS
Modulus of rupture, N/mm ²		46	C-120
Water absorption, % by weight		0.3	C-121
Acid resistance (weather resistance) Depth of softening mm		0.05	C-217
Abrasion (Resistance to wear)	Average wear, mm	2.6	IS 1237 Guidelines
	Max. wear on individual specimen	1.8	