

# Installation guidance

Thistle® MultiFinish

TIMES ARE APPROXIMATE

## 0 mins



Add approx 11.5 litres of clean water per 25kg bag to mixing bucket. Gradually add the plaster to water whilst mixing



Complete 1<sup>st</sup> coat (1mm thick)

## 20 - 45 mins



Complete 2<sup>nd</sup> coat, the total thickness for both coats should be a minimum of 2mm

## 45 - 60 mins



Closing in

## 90 mins



1<sup>st</sup> trowel

## 100 mins

2<sup>nd</sup> trowel

## 120 mins

Final trowel to a matt finish (lubricated with minimal water)

### Note:

Ensure that the product is suitable for the background to which it is being applied by using the Thistle Plaster Selector Guide.



Finishing times are **reduced** by suction



Finishing times are **extended** by cold weather conditions

**Times and processes are given as guidance. On site practice may vary.**